

Insulator-Metal transition in the Doped $3d^1$ Transition Metal Oxide $LaTiO_3$

L. Craco¹, M. S. Laad¹, S. Leoni², and E. Müller-Hartmann¹

¹*Institut für Theoretische Physik, Universität zu Köln, Zùlpicher Strasse, 50937 Köln, Germany*

²*Max-Planck-Institut für Chemische Physik fester Stoffe, 01187 Dresden, Germany*

(February 2, 2008)

The doping induced insulator-metal transition in $La_{1-x}Sr_xTiO_3$ is studied using the ab-initio LDA+DMFT method. Combining the LDA bandstructure for the actual, distorted structure found recently with multi-orbital DMFT to treat electronic correlations, we find: (i) ferro-orbital order in the Mott insulating state without orbital degeneracy, (ii) a continuous filling induced transition to the paramagnetic metal (PM) with x , and (iii) excellent quantitative agreement with published photoemission data for the case of 6% doping. Our results imply that this system can be described as a Mott-Hubbard system without orbital (liquid) degeneracy.

PACS numbers: 71.27.+a, 71.15.Mb, 79.60.-i

The early TMO $LaTiO_3$ is an interesting case of a system exhibiting filling-driven insulator-metal transition. Long thought of as a text-book example of a Mott insulator with antiferromagnetic order, current interest in orbital correlations in TMOs has reopened the subject of the physics of $LaTiO_3$ [1].

According to [2] this material with $Ti^{3+}(3d^1)$ configuration is an electron analog of the cuprates, with G -type AF spin order below $T_N \simeq 150$ K, and with a reduced spin moment in the AF state. Recent neutron scattering measurements reveal an *isotropic* magnon dispersion, with a small spin gap, $\Delta_s = 3.3$ meV, putting strong constraints on an acceptable mechanism for the observed antiferromagnetism [2]. The fact that the single electron in $LaTiO_3$ resides in the t_{2g} orbitals (less prone to Jahn-Teller distortions) suggested that the orbital moment might not be fully quenched in this case. Attempts to explain the strongly reduced spin moment of $\mu = 0.46\mu_B$ [2] assuming an unquenched orbital moment aligned antiparallel to the spin moment (spin-orbit coupling in the t_{2g} shell of Ti^{3+}) led to a spin gap much larger than that of 3.3 meV observed in INS [2], excluding an orbital contribution to the ordered moment. Moreover, ferro-orbital order (FOO) has recently been suggested [3], in complete accord with the G -type AF spin order below T_N , implying lifting of the t_{2g} orbital degeneracy.

The metallic phase in $La_{1-x}Sr_xTiO_3$ [1] has been shown to be a canonical strongly correlated Fermi liquid [1], putting additional constraints on an acceptable model for this system. In particular, this implies a non-degenerate ground state in the paramagnetic metal (PM) phase, since any remnant of orbital degeneracy (if it was hypothesized to exist) would lead to violation of Landau's Fermi liquid hypothesis, and lead to a non-FL metallic state, in contradiction with observations. AF LRO is rapidly suppressed upon Sr doping, and classic signatures of the Brinkman-Rice (BR) correlated FL are seen close to the MIT, suggesting that the AFI state is a Mott-Hubbard insulator and that the AFI-PM transition

is a Mott-Hubbard transition. Given the incomplete understanding of the AFI, the mechanism of the MIT still constitutes an open problem for theory, in spite of much recent activity [4].

Two alternatives were proposed to account for the puzzling observations in the AFI phase. Mochizuki *et al.* [5] presented a model for the AF in $LaTiO_3$ using a $GdFeO_3$ distortion, which, however, was not observed. Khaliullin *et al* [6] proposed a novel theoretical idea based on an orbital liquid, but the short-ranged orbital RVB-like fluctuations were not observed either [3]. Moreover, it has been shown recently that long range AF order is theoretically *incompatible* with an orbital liquid state [7], deepening the controversy regarding the origin of G -type AF order in $LaTiO_3$.

Here, following new work [8] pinpointing the real crystal structure (RCS) of $LaTiO_3$, we propose a detailed theoretical scenario unifying the various experimentally observed features in the insulating (I) as well as the correlated metallic (M) states. Employing the state-of-the-art technique LDA+DMFT (IPT) (combining the real bandstructure of $LaTiO_3$ with dynamical correlation effects of local Coulomb interactions), we show how a consistent description of the doping-induced insulator-metal (I-M) transition, as well as very good quantitative agreement with photoemission results is obtained.

The RCS of $LaTiO_3$ (i.e, $Pbnm$ space group) involves a structural distortion arising from the tilting of the TiO_6 octahedra around the $[110]_c$ axis followed by their rotation around c , beginning from the cubic perovskite structure. The specific distortion of the TiO_6 octahedra in $LaTiO_3$ is characterized by a large splitting in the $O2-O2$ edge lengths of the octahedral basal plane, giving rise to elongation along a and shrinking along b . This implies FOO and a lifting of t_{2g} orbital degeneracy. Starting from a local picture in the d^1 configuration, the occupied orbital is constructed as: $|a\rangle = 0.77(\frac{|xz+yz\rangle}{\sqrt{2}}) \pm 0.636|xy\rangle$, which is non-degenerate [8]. We have carried out a local density approximation (LDA) study based on the RCS described above.




FIG. 1. LDA partial densities of states (DOS) for the real crystal structure of $LaTiO_3$. Full line denotes the DOS for the non-degenerate ground-state orbital, the dotted line denotes the DOS for the higher (almost two-fold degenerate) lying t_{2g} orbitals. The dot-dashed line denotes the small e_g -DOS around E_F . Higher-lying e_g and O -2p bands are not included in the Figure.

To obtain the band DOS, the one-electron scalar relativistic Schrödinger equation was solved self-consistently within the LDA, using the linear muffin-tin orbitals (LMTO) scheme in the atomic sphere approximation, with combined correction terms [9]. The exchange-correlation potential was parametrized according to the von Barth-Hedin scheme [10,11]. Self-consistency was reached on performing calculations on a $\mathbf{k}$ -mesh of dimension $16 \times 16 \times 16$. The radii of the atoms in the real RCS were chosen to minimize their overlap. Values of $r = 3.7$ (La), $r = 2.12$ (O) and $r = 2.75$ (Ti) a.u. were found to be useful.

The total LDA density of states, $\rho(\omega) = \sum_{\mathbf{k},\alpha} \delta(\omega - \epsilon_{\alpha}(\mathbf{k}))$, with the LDA (one-electron) Hamiltonian given by

$$H_0 = \sum_{\mathbf{k},\alpha} \epsilon_{\alpha}(\mathbf{k}) c_{\mathbf{k}\alpha}^{\dagger} c_{\mathbf{k}\alpha}.$$

Several interesting points are apparent from the LDA results. First, the t_{2g} splitting is *not* negligible, and the character of the occupied ground state orbital $|\alpha\rangle$ (not shown) is in accord with the result of Ref. [8]. The LDA bandwidth of the t_{2g} bands is about 2 eV, and the charge transfer energy (LDA) is large, $\Delta_{LDA} \simeq 7.0$ eV, while the onsite Hubbard $U \simeq 6.0$ eV, putting $LaTiO_3$ in the Mott-Hubbard category, as expected [1]. Further, the Hund coupling, $J_H \simeq 1$ eV (relevant in the excited d^2 configuration, with the two d electrons on different orbitals, realized upon $d-d$ hopping), and the inter-orbital coupling, $U' = (U - 2J_H) \simeq 4.0$ eV. These results (see

Fig. 1) do not represent an insulating state, this requiring a proper treatment of correlation effects in the RCS. Given the FOO found in $LaTiO_3$, a description in terms of a single-band model for the $|\alpha\rangle$ band is untenable, and requires a full multi-orbital dynamical mean field calculation. To avoid double counting of interactions already treated on the average by LDA, we follow [4] to write,

$$H'_0 = H_0 + \sum_{i,\alpha\sigma} \epsilon_{i\alpha\sigma}^0 n_{i\alpha\sigma},$$

with $\epsilon_{i\alpha\sigma}^0 = \epsilon_{i\alpha} - U(n_{i\alpha-\sigma} - \frac{1}{2}) + \frac{J_H}{2}(n_{i\alpha\sigma} - 1)$.

The full many-body Hamiltonian is now given by,

$$H = H'_0 + U \sum_{i,\alpha} n_{i\alpha\uparrow} n_{i\alpha\downarrow} + U' \sum_{i\alpha\beta} n_{i\alpha} n_{i\beta} - J_H \sum_{i\alpha\beta} \mathbf{S}_{i\alpha} \cdot \mathbf{S}_{i\beta}.$$

We solve this multiband model in $d = \infty$ using multi-orbital iterated perturbation theory (IPT) [12]. Assuming no symmetry breaking in the spin/orbital sectors, we have $G_{\alpha\beta\sigma\sigma'}(\omega) = \delta_{\alpha\beta} \delta_{\sigma\sigma'} G_{\alpha\sigma}(\omega)$ and $\Sigma_{\alpha\beta\sigma\sigma'}(\omega) = \delta_{\alpha\beta} \delta_{\sigma\sigma'} \Sigma_{\alpha\sigma}(\omega)$. Further, from the LDA results, the DOS for the e_g bands is small near E_F . Taking this together with the fact that the $O - 2p$ bands lie 6 eV away from E_F , we keep only the t_{2g} bands in what follows.

The DMFT solution involves [13] (i) replacing the lattice model by a self-consistently embedded multi-orbital, asymmetric Anderson impurity model, and, (ii) the self-consistency condition requiring the local impurity Green function to be equal to the local GF for the lattice. In $LaTiO_3$, in the $3d^2$ configuration reached by hopping, U' , J_H scatter electrons between different t_{2g} orbitals, so only the *total* number, $n_{t_{2g}}^d = \sum_{\alpha} n_{t_{2g},\alpha}^d$ is conserved in a way consistent with Luttinger's theorem. The calculation follows the philosophy of the one-orbital IPT, with the GFs and the self-energies being matrices in the orbital indices. The full set of equations for the multi-orbital case are the same as those appearing elsewhere [14], and we do not reproduce them here. Local self-energies computed from this generalized IPT formulation exactly satisfy the Friedel-Luttinger constraint for arbitrary band-fillings, guaranteeing the correct low-energy form of the spectral function. The correct form of the spectrum at high energy is ensured by the (exact) selfconsistent determination of the first few moments of the spectral function. These equations are solved selfconsistently with the LDA DOS as input, until convergence is achieved.

We now present our results. Figure 2 shows the total spectral function for the paramagnetic insulating (PI) state of $LaTiO_3$. This does not correspond to the true ground state, which is a G -type AFI, but to the PI (Mott) state above T_N . The Mott-Hubbard gap is read off directly from the DOS as $\Delta_G^I \simeq 0.4$ eV. Further, the renormalized value of the t_{2g} splitting is computed to




FIG. 2. LDA+DMFT results for the partial DOS in the insulating state, obtained using $U = 6.0$ eV, $J_H = 1.0$ eV, and $U' = 4.0$ eV in the real bandstructure of $LaTiO_3$.

be 0.15 eV, implying a reduction in the charge transfer energy, $\Delta_{ct} = (\epsilon_p - \epsilon_d)$ from 7.0 eV in the LDA to 6.64 eV in the correlated solution. This is likely to be an overestimate, since further downward renormalization of Δ_{ct} will result from additional Hartree shifts arising from inclusion of Madelung ($p-d$ interaction) terms. These results constitute a concrete resolution of the questions posed recently [15], namely, the mechanism for the generation of a small-gap Mott-Hubbard insulator in a situation where the Coulomb interactions are comparable to the LDA bandwidth. In view of our results, dynamical effects of coupled spin/orbital correlations in the real structure of $LaTiO_3$ are of crucial importance for a consistent resolution of this issue. We also find the occupation of the lowest t_{2g} orbital, $n_{|\alpha\rangle} = 0.17$, slightly higher than that of the other two higher-lying (by 0.15 eV) orbitals in the t_{2g} sector.

These results are consistent with having ferro-orbital order (FOO) in $LaTiO_3$ [3]. Further, since the ground state occupied orbital, $|\alpha\rangle = a_1|xz + yz\rangle + a_2|xy\rangle$ (consistent with Ref. [8]) is *not* oriented along one of the bonds, the resulting AF exchange is not expected to be very anisotropic. A detailed calculation of the Heisenberg superexchange based on the LDA+DMFT results, along with proper incorporation of spin anisotropies, is in progress and will be reported elsewhere.

To model the paramagnetic metallic (PM) state, reached (continuously from the PI in our approach) upon doping $LaTiO_3$ with Sr , we extended our calculation for the PI to: (i) incorporate the change in band-filling along the same lines as for generalized IPT for the single band case. This implies computing the chemical potential shift, as required by Luttinger's theorem, and, (ii) considering the effects of Sr doping induced static disorder

(the difference of the on-site potentials on Sr substitution is $\Delta v \simeq 4.0$ eV [16]) using the coherent-potential approximation (CPA) combined selfconsistently [17] with the multi-orbital IPT described above. Furthermore, to obtain quantitative consistency with spectroscopic results, we found it necessary to include the (small near E_F) DOS of the e_g bands found in the LDA (Fig. 1), as well (see below).

Generically, hole doping the (Mott) PI creates a very sharp, quasicohherent Fermi liquid peak at the renormalized E_F , with dynamical spectral weight transfer over a large energy scale from high to low energy (caused by U, U', J_H within DMFT), driving a first-order Mott transition in the generic case. In this situation, static, potential disorder is expected to lead to a moderate broadening of the sharp FL peak, with spectral weight transfer from low to high energy [17], and, more importantly, to convert the first-order Mott transition into a continuous one. Thus, the character of the MIT, as well as details of the actual one-particle spectrum depend sensitively on how the competition between Mott-Hubbard localization and itinerance in a multi-band system is affected by doping induced static disorder.

With this in mind, we show the photoemission (PES) and inverse-PES (IPES) spectra for the lightly ($\delta \equiv x+y = 0.06$) doped, PM state of $La_xSr_{1-x}TiO_{3+y/2}$ [18], along with the experimental result for $I_{PES}(\omega)$ in Fig. 3. Clearly, excellent quantitative agreement between theory and experiment is found over the entire range $-2 \leq \omega \leq E_F$. In particular, the lower Hubbard band, the quasicohherent FL feature, as well as the details of the lineshape are all in excellent agreement with experiment. In the IPES spectrum, we are able to resolve the α, β peaks




FIG. 3. The photoemission (PES) and inverse photoemission (IPES: in inset) spectra for both, pure (dashed) and doped (solid) $LaTiO_3$. Excellent quantitative agreement with experimental results (PES: squares) of Ref. [18] is clear.

along with the much greater signal intensity and the correct detailed form of the lineshape [19]. Thus, our results represent a *quantitatively* accurate representation of the complete one-electron spectral function in the PM phase of $La_{1-x}Sr_xTiO_{3+y/2}$. Lastly, from the Fermi liquid self-energies (not shown), the effective mass renormalization is estimated to be $m^*/m_b = 1.5$ for $\delta = 0.06$ in good quantitative agreement with the frequency-dependent renormalization estimated from PES [18]. Actually, the total renormalization includes additional renormalization (factor of 2) coming from the $\mathbf{k}$ -dependence of the self-energies. On general grounds, we do expect such renormalization in a case of proximity to the AF transition; theoretically, an extension to include non-local correlations is required to address this issue. We have not done this here.

We stress essential differences between our work and earlier works. In Ref. [4,5], an incorrect crystal structure was used for the LDA calculation. Moreover, the strong $J_H \simeq 1.0$ eV along with the inter-orbital U' seem to have been completely ignored in their correlation (DMFT) calculations. Turning to Ref. [6], we believe, given the fact that a multitude of experiments reveal correlated (Brinkman-Rice) FL responses (PM), that the basic Landau hypotheses force one to abandon a picture based on orbital degeneracy in the PM phase as well. We re-emphasize that AF-LRO has recently been shown to be impossible [7] for a $3d^1$ system with triple orbital (t_{2g}) degeneracy. Very recently, Pavarini *et al.* [21] have studied a host of $3d^1$ systems within LDA+DMFT, obtaining similar conclusions for the Mott insulating state in $LaTiO_3$. However, the Sr -doping induced I-M transition has not been studied there. Additionally, using QMC to solve the DMFT equations forces a restriction to high- $T = 770$ K [21]. Given the strong T dependence of the correlated Fermi liquid scale within DMFT, as well as the much lower FL coherence scale observed experimentally in doped $LaTiO_3$ [1,13], (in contrast to QMC results), we believe that a quantitative comparison with experiment at low T requires the solution of the DMFT equations at lower $T \simeq 150$ K, as we have done. Finally, we draw attention to the excellent quantitative agreement between theory and experiment for the one-electron spectral function, obtained using LDA+ (multi-orbital) DMFT. To our knowledge, this is the first calculation achieving such unprecedented agreement between experiment and theory for this system.

To conclude, we have studied the doping induced Mott transition in the $3d^1$ system $La_{1-x}Sr_xTiO_3$ using the ab-initio LDA+DMFT method. Starting from the real crystal structure (with lifting of t_{2g} orbital degeneracy), we have explicitly demonstrated the nature of the carrier driven MIT in this system. Our results support ferro-orbital order in the insulating state, consistent with recent suggestions [3], and with the observed G -type AF order. In conjunction with [8, 21], these results favor a

description of the physics of $LaTiO_3$ in a picture of non-degenerate t_{2g} orbitals. Within this picture, in the PM state, excellent quantitative agreement with published PES and IPES results is obtained, providing a complete description of the evolution of one-particle excitations across the MIT. Similar ideas can be fruitfully applied to study the doping-driven MI transitions in other TMO-based systems [20] with coupled spin-orbital correlations.

ACKNOWLEDGMENTS

MSL and LC acknowledge fruitful discussions with D. I. Khomskii in course of this work. SL wishes to acknowledge A. Yaresko for his help with the LMTO program and for valuable discussions. Work carried out under the auspices of the Sonderforschungsbereich 608 of the DFG (Köln), and the MPI-CPfS (Dresden).

-
- [1] M. Imada, A. Fujimori, and Y. Tokura, *Revs. Mod. Phys.* **70**, 1039 (1998).
 - [2] B. Keimer *et al.*, *Phys. Rev. Lett.* **85**, 3946 (2000).
 - [3] V. Fritsch *et al.*, *Phys. Rev. B* **65**, 212405 (2002).
 - [4] V. I. Anisimov *et al.*, *J. Phys. Cond. Mat.* **9**, 7359 (1997).
 - [5] G. Mochizuki *et al.*, *J. Phys. Soc. Jpn.* **70**, 2872 (2001).
 - [6] G. Khaliullin and S. Maekawa, *Phys. Rev. Lett.* **85**, 3950 (2000).
 - [7] A. B. Harris *et al.*, *cond-mat/0307515*.
 - [8] M. Cwik *et al.*, *Phys. Rev. B* **68**, 060401 (2003).
 - [9] O.K. Andersen, *Phys. Rev. B* **12**, 3060 (1975); Hans L. Skriver, *The LMTO Method*, (Springer series in solid state sciences 41, Springer, Berlin 1984).
 - [10] U. von Barth and L. Hedin, *J. Phys. C* **5**, 1629 (1972).
 - [11] A. Perlov, A. Yaresko, and V. Antonov, Program LMTO, version 4.05.6, MPIPES Dresden, 2003.
 - [12] L. Craco, M. S. Laad, and E. Müller-Hartmann, *Phys. Rev. Lett.* **90**, 237203 (2003).
 - [13] A. Georges *et al.*, *Rev. Mod. Phys.* **68**, 13 (1996).
 - [14] I. A. Nekrasov *et al.*, *Eur. Phys. Journal. B* **18**, 55, (2000).
 - [15] P. Lunkenheimer *et al.*, *cond-mat/0307333*.
 - [16] D. D. Sarma *et al.*, *Europhys. Lett.* **36**, 307 (1996).
 - [17] M. S. Laad, L. Craco, and E. Müller-Hartmann, *Phys. Rev. B* **64**, 195114 (2001).
 - [18] T. Yoshida *et al.*, *Europhys Lett.* **59**, 258 (2002).
 - [19] M. Abbate, F. M. F. de Groot, and J. C. Fuggle, *Phys. Rev. B* **44**, 5419 (1991).
 - [20] K. Morikawa *et al.*, *Phys. Rev. B* **54**, 8446 (1996).
 - [21] E. Pavarini *et al.*, *cond-mat/0309102*.